

## PRODUCT INFORMATION



# PROMIX<sup>®</sup> 750

**APPLICATION:** General processing and dispersion aid for most synthetic and natural elastomers. Especially effective as a homogenizing agent for dissimilar elastomers.

**COMPOSITION:** A blend of dark aliphatic, naphthenic, aromatic hydrocarbon resins.

### TYPICAL CHARACTERISTICS

<b><u>APPEARANCE:</u></b>	Black pellets
<b><u>SPECIFIC GRAVITY:</u></b>	Approximately 1.06 ± 0.03
<b><u>SOFTENING POINT:</u></b>	90 ± 5 C
<b><u>% EVAPORATION LOSS:</u></b>	0.5% maximum (@ 105°C for 2 hours)
<b><u>SOLUBILITY:</u></b>	Soluble in aromatic solvents
<b><u>ASH CONTENT:</u></b>	2.7 maximum
<b><u>STORAGE STABILITY:</u></b>	Minimum of one year under normal conditions
<b><u>PACKAGING:</u></b>	25 kg polyethylene bags
<b><u>RECOMMENDED USE:</u></b>	6 - 15 phr. Add with first addition of fillers.

### ADVANTAGES

- Excellent wetting agent to decrease mixing time of fillers
- Improves general processing properties of highly filled synthetic and natural elastomer compounds
- Improves compatibility in multiple polymer systems

Revised: May 6, 2003/PROMIX 750